



RAINBOW

ADHESION PROMOTERS FOR SEALER

PRODUCT NUMBER	NO.467AD
TYPE	The Adhesion promoters based on excellent water-modified polymer with a special micron-grade additives.
USES	With NO.467 Water Based Penetrating Waterproof Sealer to use.
CHARACTERISTICS	The following characteristics are NO.467 and NO.467AD evenly mixed effects: <ol style="list-style-type: none">1. Hybrid composite structure: paint coating + infiltration of crystals to form a double waterproof protective layer.2. I.E. ion exchange crystallization technology: penetrate into the substrate gap for ion exchange to produce crystalline complete block water and moisture.3. M.P. Micromolecule Closure Technology: Micro-molecules effectively bond substrates and bind tightly.4. Multi-substrate, easy to complete.
COLOR	transparent
MASS DENSITY	Above 1.02 Kg/L
DRYING TIME	Set-to-touch 1/2 hr. Dry hard 3 hrs. (25°C)
THEORETICAL COVERAGE	50.3 m ² /Gal 13.3 m ² /L
OVERCOATING INTERVALS	Min. 4 hrs.
PACKAGE WEIGHT	2 liters, 10 liters
SUBSEQUENT COATS	NO.424 · NO.421 · NO.406 · SA2000 · SA3000 · SA5000 · NO.8513.
ADHESION PROMOTERS	1 gallon NO.467 with 2 liters NO.467AD
RECOMMENDED DOSAGE	5 gallon NO.467 with 10 liters NO.467AD
STORAGE SHELF LIFE	Minimum 3 years under normal storage conditions.
APPLICATION METHOD	Spray, Brush, Roller.
INSTRUCTIONS	<ol style="list-style-type: none">1. Before application, stir paint evenly, To be painted surface of the grease, dust, moisture and other contaminants, must be cleaned before construction.2. After mixing without additional water dilution, can be directly coated on the substrate.3. After mixing, please use the same day to avoid deterioration.
PRECAUTIONS	<ol style="list-style-type: none">1. Avoid direct contact with the eyes, mouth, nose, should wear appropriate protective equipment.2. After mixing thoroughly stir, to ensure NO.467 and NO.467AD to achieve the best product results.3. Please store the product in a cool and ventilated place, do not place it in the sun can be irradiated area.4. To be painted surface wet and rainy days should avoid construction, to ensure construction quality.5. Drying time will vary depending on paint thickness, substrate type, ambient humidity, ventilation conditions.
NOTE	The actual brushing area will be affected by the nature of the substrate, the substrate surface conditions, construction tools and other environmental factors.

EPDM410467AD V1.3

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443