



RAINBOW

RAINBOW C.R. TAR PAINT

NO	No.1455
TYPE	Anti-corrosive paint based on Chlorinated Rubber, refined Coal Tar and aluminum pigment.
USES	Anti-corrosive under coat for ship bottom and boottop areas, especially suitable for the pipes of under floor.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying with very good adhesion.2. Very good weather resistance.3. Very good resistance to seawater.4. Tough and flexible.5. Good resistance to galvanic action.6. Relatively low cost.
APPLICATION METHOD	Brush, Roller, Airless Spray.
COLOR	Black or Reddish Silver
FINISH	Flat
HILDING POWER	Above 20 m ² /L
SPECIFIC GRAVITY	Above 1 kg/L
VISCOSITY (25)	60 ~ 80 KU
DRYING TIME (25)	Set-to-touch 1 hr. Dry hard 3 hrs.
OVERCOATING INTERVALS (25)	Min. 4 hrs. Max. 4 months.
OPTIMUM FILM THICKNESS	Wet 105 microns (4.2 mil) Dry 50 microns (2.0 mil)
VOLUME SOLIDS	Above 60%
THEORETICAL COVERAGE	9.5 m ² /L 9.5 m ² /KG 36 m ² /Gal
THINNER	RP-71 PCR Thinner
THINNING RATE	0 ~ 5 %(by wt.)
PRECEDING COATS	No.908/1021
SUBSEQUENT COATS	Protective C.R. A/F
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
NOTE	<ol style="list-style-type: none">1. Before application, stir paint evenly. When paint is too thick, thinner can be added within specified quantity2. Moisture, grease, rust, dirt and loose paints film on substrate must be removed, so are the corrosive salt particles. As a result, paint performance can be ensured.3. Application should avoid the following environment: rainy day; substrate is damp by dew; temperature is above 40°C or below 10°C.4. Subsequent coat has to wait until paint films of preceding coat completely dry off.

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443