



RAINBOW

RED OXIDE PRIMER

PRODUCT NUMBER	SP-56 (OP-95)
TYPE	Anti-corrosive paint based on alkyd and special resins with red oxide pigment.
USES	Anti-corrosive primer for steel structures, another economical choice.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying with good adhesion.2. Very good resistance to weather and abrasion.3. Good resistance to water.4. Easy application.5. Economical cost.
COLOR	Oxide red
FINISH	Flat
HIDING POWER	Above 1.2 m ² /L
SPECIFIC GRAVITY	Above 1.3 Kg/L
VISCOSITY	70 ~ 85 KU (25°C)
DRYING TIME	Set-to-touch 1 hr. Dry hard 4 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 90 microns Dry 40 microns
THEORETICAL COVERAGE	41 m ² /Gal 11.0 m ² /L 8.5 m ² /Kg
OVERCOATING INTERVALS	Min. 6 hrs. (25°C)
VOLUME SOLIDS	Above 44 %
THINNER	No.805 Paint Thinner (OM-07)
THINNING RATE	5~10 % (cleaning tools excluded)
PRECEDING COATS	No.908 Wash Primer (SP-01/02) No.905 High Red Lead Primer (OP-91)
SUBSEQUENT COATS	Alkyd topcoats
STORAGE SHELF LIFE	Minimum 3 years under normal storage conditions.
APPLICATION METHOD	Airless Spray, Brush, Roller
NOTE	<ol style="list-style-type: none">1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.3. When substrate is damp with dew or during rainy weather, painting must be suspended.4. Avoid applying to insufficient drying of previous paint coat.

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443