



RAINBOW

BITUMINOUS SOLUTION

PRODUCT NUMBER	607
TYPE	The varnish based on coal tar and asphalt.
USES	Used for steel to anti-rust and wood to mothproof.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying.2. Very good water and corrosion resistance.3. Easy application.
APPEARANCE	Black liquid
MASS DENSITY	Above 0.85 Kg/L
DRYING TIME	Set-to-touch 1/2 hr. Dry hard 3hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 70 microns Dry 25 microns
THEORETICAL COVERAGE	54.0 m ² /Gal 14.3 m ² /Kg 16.8 m ² /Kg
OVERCOATING INTERVALS	Min. 3hrs.
VOLUME SOLIDS	Above 36%
THINNER	No.805 Paint Thinner (OM-07)
THINNING RATE	0~5% (cleaning tools excluded)
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Brush, Roller, Airless Spray.
NOTE	This paint film can not be applied any paint or varnish to avoid asphalt permeating out.

EPDM060607XX V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443