



# RAINBOW

## RAINBOW C.R. B/T

PRODUCT NUMBER	SP-18 / SP-19 ( RB-21~ 22 )
TYPE	The boottop paint based on chlorinated rubber with weather resistant pigment.
USES	Topcoat for boottop areas.
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Very fast drying with excellent adhesion.</li><li>2. Very good resistance to sea water.</li><li>3. Very good resistance to mechanical damage.</li><li>4. Very good resistance to weather.</li><li>5. Very good resistance to floating oil on the sea.</li></ol>
FINISH	Semi-Gloss
COLOR	SP-18 : Red oxide / SP-19 : Green
FLASH POINT	Above 26°C (80°F)
SPECIFIC GRAVITY	Above 1.25 Kg/L
VISCOSITY	70 ~ 85 KU (25°C)
DRYING TIME	Set-to-touch 1/2 hr.      Dry hard 2 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 85 microns (3.4 mil)      Dry 35 microns (1.4 mil)
THEORETICAL COVERAGE	44.6 m <sup>2</sup> /Gal      11.8 m <sup>2</sup> /L      9.4 m <sup>2</sup> /Kg
OVERCOATING INTERVALS	Min. 4 hrs. (25°C)
VOLUME SOLIDS	Above 41 %
THINNER	No.1407 PCR Thinner ( RP-71 )
THINNING RATE	5~10 % (cleaning tools excluded)
PRECEDING COATS	SP-16 Rainbow C.R. A/C ( RA-11 )
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Airless Spray, Brush, Roller
NOTE	<ol style="list-style-type: none"><li>1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.</li><li>2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.</li><li>3. When substrate is damp with dew or during rainy weather, painting must be suspended.</li></ol>

**YUNG CHI PAINT & VARNISH MFG.CO.,LTD**

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181      FAX : 886-7-8715443