



# RAINBOW

## RAINBOW C.R. A/C

PRODUCT NUMBER	SP-16 (RA-11)
TYPE	Anti-corrosive paint based on chlorinated rubber with aluminum pigment.
USES	Anti-corrosive primer for ship bottom, boottop and topside areas.
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Fast drying with excellent adhesion.</li><li>2. Excellent resistance to weather.</li><li>3. Excellent resistance to sea water and oil.</li><li>4. Excellent resistance to mechanical damaged.</li><li>5. Very good resistance to galvanic action.</li></ol>
FINISH	Semi-gloss
COLOR	Silver, Reddish silver
FLASH POINT	Above 26°C (80°F)
SPECIFIC GRAVITY	Above 1.2 Kg/L
VISCOSITY	70 ~ 90 KU (25°C)
DRYING TIME	Set-to-touch 1/2 hr.                      Dry hard 2 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 100 microns (4.0 mil)              Dry 40 microns (1.6 mil)
THEORETICAL COVERAGE	37.9 m <sup>2</sup> /Gal              10.0 m <sup>2</sup> /L              8.3 m <sup>2</sup> /Kg
OVERCOATING INTERVALS	Min. 3 hrs. (25°C)
VOLUME SOLIDS	Above 40%
THINNER	No.1407 CR Thinner (RP-71)
THINNING RATE	5 ~ 10% (cleaning tools excluded)
PRECEDING COATS	No.1021 Cathozinc Shop Primer (SP-09) SP-08 Non-zinc Shop Primer No.908 Wash Primer (SP-01/02) No.1006 Epoxy Zinc Rich Primer (EP-03)
SUBSEQUENT COATS	CR paints, oleoresinous paints, ship bottom paint
STORAGE SHELF LIFE	Minimum 6 months under normal storage conditions.
APPLICATION METHOD	Airless Spray, Brush, Roller
NOTE	<ol style="list-style-type: none"><li>1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.</li><li>2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.</li><li>3. Avoid applying the paint in rainy or humid weather.</li></ol>

**YUNG CHI PAINT & VARNISH MFG.CO.,LTD**

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181    FAX : 886-7-8715443