



# RAINBOW

## RAINBOPRIME 804LT

Polyamide Cured Epoxy ( Low-Temp )

PRODUCT NUMBER  
TYPE

RAINBOPRIME 804LT

The two-pack, universal anticorrosion primer based on epoxy resin, hardener and special pigments.

CHARACTERISTICS

1. Used for the new building system or the maintenance system, including ship's all areas such as ballast tank, underwater hull, topside, deck, cargo tank, oil tank, superstructure, interior etc. Also used for anticorrosion engineering of steel structure such as chemical factories, bridges, power plants, inlet and outlet pipes, drains and sewers etc.
2. Simplified procedure, convenient application, unique long terms anticorrosive performance.
3. Excellent anticorrosion and adhesion, widely apply on shop primer, steel plate (sand-blasted or mechanical surface preparation), aluminum, stainless steel, galvanized steel preparation.
4. Can be coated a variety types of coating, e.g. epoxy, polyurethane, acrylic, alkyd, chlorinated rubber, vinyl and fire retardant paint.
5. Excellent resistance to mechanical damage.
6. Excellent resistance to sea water when applied to steel and non-ferrous metal.
7. Easy application, very fast drying, it's good for all seasons to use.

GLOSS

Flat

COLOR

Yellowish Green, Grey, Red Oxide

VOC

Max. 424 g/L

PRODUCT WEIGHT

Above 1.3 Kg/L

DRYING TIME

Set-to-touch 3 hrs. Dry hard 6 hrs. (25°C)

OPTIMUM FILM THICKNESS

Wet 125~333 microns Dry 75~200 microns

VOLUME SOLIDS

60±2%

THEORETICAL COVERAGE

30.3 m<sup>2</sup>/Gal 8 m<sup>2</sup>/L @ 75 microns

OVERCOATING INTERVALS

Overcoating table for two-pack epoxy coating:

Substrate temperature	-10°C	-5°C	0°C	10°C	15°C
Minimum	48 hours	24 hours	16 hours	6 hours	4 hour
Max. (direct exposed to sunshine)	2 months	2 months	2 months	1 month	1 month
Max. (not exposed to sunshine)	3 months	3 months	3 months	2 months	1 month

MIXING RATIO

Base : Hardener = 16 : 4 (by volume)

POT LIFE

7 hrs. (10°C)

THINNER

No.1005 Epoxy Thinner ( SP-12 )

THINNING RATE

Brush / Roller : 0~5% Airless spray : 0~10% (Max. limited)

RECOMMENDED SPEC.

Please refer the painting specification

STORAGE SHELF LIFE

Minimum 1 year under normal storage conditions.

APPLICATION METHOD

Airless Spray, Brush, Roller

NOTE

1. Mix base and hardener according to the mixing ratio and stir thoroughly.
2. Adhered moisture, salt, grease, sludge, dust and rust on substrate must be removed thoroughly.
3. Surface of steel must be pretreated by sand-blasting to ISO-Sa 2 1/2 roughness up to 30 microns or with high pressure water-jet to VIS WJ 2/3.
4. Surface of shop primer must be pretreated by sand-sweeping to ISO SS or St3.
5. Avoid applying the paint in raining weather or the relative humidity exceeded 85%RH or substrate temperature below the dew point 3°C.
6. When used inside tanks, sufficient ventilation must be provided.

EPDM3030804L V1.1

# YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.  
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181  
FAX:886-7-8715443