



RAINBOW

RAINBOLIC 25

Acrylic Finish

PRODUCT NUMBER	RAINBOLIC 25
TYPE	Modified Acrylic finish
CHARACTERISTICS	<ol style="list-style-type: none">1. Finish coat for above water areas2. Good resistance to sea water .3. Good gloss and color retention.4. Fast drying.5. Easy application
GLOSS	Gloss
COLORS	White and various other colours.
VOLATILE ORGANIC COMPOUND CONTENT	VOC 450 (g/l) below
PRODUCT WEIGHT	Above 1.1 kg/L
DRYING TIME	Set-to-touch 1 hrs Dry hard 4 hrs (25°C) (35 μ)
OPTIMUM FILM THICKNESS	Wet 78 ~ 167μ (Micron) Dry 35 ~ 75μ (Micron)
VOLUME SOLID	45 ±2%
THEORETICAL COVERAGE	50.5 m ² /Gal 13.3 m ² /L @ 35μ
OVERCOATING TABLE	least 3 hours (25°C) □
THINNER	RP-71 rubber thinner
THINNER RATE	0~2% (by bush and roller) 0~3% (Airless)
RECOMMENDED SPEC.	Please refer the painting specification
SHELF LIFE	Minimum two years under normal storage condition
APPLICATION METHOD	Airless spray, Bush and Roller
NOTE	<ol style="list-style-type: none">1. Adhered water, grease and dust on substrate must be thoroughly clean.2. Substrate temperature should be 3°C above dew point, rainy day and relative humidity during application and curing should be below 85%, or job is to be stopped.3. Whilst application in the confine space, adequate ventilation must be maintenance.

EPDM3030025X V1.2

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443