



RAINBOW

RED OXIDE SURFACER, GENERAL PURPOSE

PRODUCT NUMBER	910
TYPE	Lower cost rust prevention primer based on phenolic resin and special resin with iron oxide pigment.
USES	Used for vehicles and mechanical facilities for a large quantity use.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying.2. Excellent resistance to adhesion and abrasion.3. Good rust resistance.4. Relatively low cost.
FINISH	Flat
COLOR	Red
HIDING POWER	Above 12.5 m ² /L
MASS DENSITY	Above 1.3 Kg/L
VISCOSITY	80~100 KU (25°C)
DRYING TIME	Set-to-touch 15 minutes Dry hard 2 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 90 microns Dry 40 microns
THEORETICAL COVERAGE	42.0 m ² /Gal 11.1 m ² /L 8.2 m ² /Kg
OVERCOATING INTERVALS	Min. 3 hrs.
NON-VOLATILE CONTENT	Above 65%
THINNER	No.805 Paint Thinner (OM-07)
THINNING RATE	5~10% (cleaning for tools not included)
PRECEDING COATS	No.908 Wash Primer (SP-01/02)
SUBSEQUENT COATS	No.903 Gray Surfacers, Ready-Mixed Paints, Synthetic Enamels, Hammer Tone Paints
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Spray, Brush, Roller
NOTE	<ol style="list-style-type: none">1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.3. Avoid applying the paint in rainy, humid weather or substrate temperature excessively high to 40°C or low to 10°C.4. Avoid applying to insufficient drying of previous paint coat.

EPDM090910XX V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443