



RAINBOW

RAINBOW C.R. M.I.O. PRIMER

NO.	No.1452(RP-68)
TYPE	Anti-corrosive paint based on Chlorinated Rubber, Micaceous Iron Oxide and Aluminum pigments.
USES	Heavy duty intermediate primer for bridges, tanks and steel structures, superstructures.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying with good adhesion.2. Good resistance to oil and water.3. Very good resistance to ultraviolet ray penetration.4. Easy application.
APPLICATION METHOD	Brush, Roller, Airless Spray.
COLOR	Reddish Silver
FINISH	Flat
HILDING POWER	Above 20 m ² /L
SPECIFIC GRAVITY	Above 1.4 kg/L
DRYING TIME (25°C)	Set-to-touch 1 hr. Dry hard 3 hrs.
OVERCOATING INTERVALS (25°C)	Min. 4 hrs.
OPTIMUM FILM THICKNESS	Wet 125 microns Dry 50 microns
VOLUME SOLIDS	Above 60%
THEORETICAL COVERAGE	8.0 m ² /L 5.7 m ² /KG 30 m ² /GL
THINNER	RP-71 PCR Thinner
THINNING RATE	0 ~ 5 %(by wt.)
PRECEDING COATS	No.1006/1402/1457
SUBSEQUENT COATS	Chlorinated Rubber or Alkyd topcoats.
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
NOTE	<ol style="list-style-type: none">1. Before application, stir paint evenly. When paint is too thick, thinner can be added within specified quantity2. Moisture, grease, rust, dirt and loose paints film on substrate must be removed, so are the corrosive salt particles. As a result, paint performance can be ensured.3. Application should avoid the following environment: rainy day; substrate is damp by dew; temperature is above 40°C or below 10°C.4. Subsequent coat has to wait until paint films of preceding coat completely dry off.

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443