



# RAINBOW

## RAINBOW C.R. RED LEAD PRIMER

NO.	No.1402(RP-63)
TYPE	Anti-corrosive paint based on Chlorinated Rubber with red lead pigment.
USES	Anti-corrosive under coat for topside areas, steel decks, superstructures and weathering steel structure for petro-chemical facilities, oil refineries and coastal facilities.
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Very fast drying.</li><li>2. Very good rust preventive property.</li><li>3. Very good adhesion and weather resistance.</li><li>4. Good resistance to mechanical damage.</li><li>5. Good resistance to water.</li></ol>
APPLICATION METHOD	Brush, Roller, Airless Spray.
COLOR	Orange
FINISH	Flat
HILDING POWER	Above 8 m <sup>2</sup> /L
SPECIFIC GRAVITY	Above 1.4 kg/L
VISCOSITY (25°C)	70 ~ 100 KU
BANDING TEST	6m/m φ
SALT WATER TEST	NaCl(3%) for 144 hrs.
DRYING TIME (25°C)	Set-to-touch                      1 hr. Dry hard                              3 hrs.
OVERCOATING INTERVALS (25°C)	Min.                                      3 hrs.
OPTIMUM FILM THICKNESS	Wet                                      100 microns Dry                                        40 microns
VOLUME SOLIDS	Above 62%
THEORETICAL COVERAGE	10.0 m <sup>2</sup> /L    7.1 m <sup>2</sup> /KG    37.8 m <sup>2</sup> /GL
THINNER	RP-71 PCR Thinner
THINNING RATE	0 ~ 5 %(by wt.)
PRECEDING COATS	No.908 Wash Primer
SUBSEQUENT COATS	No.1401/1404/1405/1406/1451Chlorinated Rubber topcoats.
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
NOTE	<ol style="list-style-type: none"><li>1.Before application, stir paint evenly, and when paint is too thick, CR thinner within specified quantity can be added.</li><li>2.Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.</li><li>3.When substrate is damp with dew or during rainy weather, painting must be suspended.</li><li>4.For heavy duty chemical resistant applications two coats of both primer and topcoat must be coated to insure effective resistance to acids and alkalis.</li></ol>

**YUNG CHI PAINT & VARNISH MFG.CO.,LTD**

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181    FAX : 886-7-8715443