## COPPER FREE TIN FREE SELF-POLISHING

PRODUCT NUMBER SP-99CF

**TYPE** A copper free tin free A/F based on special acrylic resin for aluminium ship

**USES** For aluminium ship bottom

**CHARACTERISTICS** 1. Dry fast . Easy application.

2. non cuprous oxide can not affect aluminium ship .

3. non tin compounds can not pollution ocean .

**FINISH** Flat

COLOR Dark Brown Above 26 °C FLASH POINT

SPECIFIC GRAVITY 1.4 kg/L Above

VISCOSITY 85 KU Above

**DRYING TIME** Set-to-touch 1hr below Dry hard 4 hrs

**OPTIMUM FILM THICKNESS** Wet 200 μ Dry 100 µ

18 m³/Gal THEORETICAL COVERAGE 5 m²/L OVERCOATING INTERVALS 6 hrs Min

**THINNER** xylene

 $0 \sim 5 \%$  (by wt.) THINNING RATE

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

APPLICATION METHOD Airless Spray, Brush, Roller

NOTE 1. Mix base and rate according to maker standard stir thoroughly.

2. Moisture, grease, sludge, old paint and rust must be thoroughly removed from substrate.

3. Akoid applying the paint in rainy or humio weather or substrate excessively high to 40°C or

low to  $10^{\circ}$ C.

4. Avoid applying to insufficient drying of previous paint coats.

EPDM31SP99CF V1.0