## VINYL ESTER GLASS FLAKE LINING, HT

PRODUCT NUMBER 1612HT

**TYPE** The high temperature resistance coating based on unsaturated polyester resin

and glass flake.

**USES** The coating used for tanks lining to resistance acids, alkalis, water solvents etc.

**CHARACTERISTICS** 1. Hard film, smooth, seamless with impermeable.

> 2. Excellent resistance to chemicals, special suitable for serious corrosive environment.

3. Good adhesion to metal or cement substrates, no cracking and no peeling.

4. Paint film did not be deformed by hot or cold temperature difference.

5. High temperature resistance to 180°C instantly.

COLOR White, Red Brown, Grey

SPECIFIC GRAVITY Above 1.10 Kg/L

Above 45000 cps (25°C) VISCOSITY

**DRYING TIME** Set-to-touch 2 hrs. Dry hard 8 hrs. (25°℃)

**OVERCOATING INTERVALS** Min. 8 hr. Max. 3 days **OPTIMUM FILM THICKNESS** Dry 250 um Wet 250 um

 $0.55 \text{ Kg/m}^{2}, 7.57 \text{ m}^{2}/\text{Gal}$  (500 um);  $1.30 \text{ Kg/m}^{2}, 3.78 \text{ m}^{2}/\text{Gal}$  (1 mm) THEORETICAL COVERAGE

**MIXING RATIO** Base: Initiator = 100: 1 (by wt.)

**THINNER** Acetone, MIBK (only for rinsing tools)

**POT LIFE** Within 60 minutes  $(30^{\circ}\text{C})$ ; Within 80 minutes  $(25^{\circ}\text{C})$ 

NON-VOLATILE CONTENT  $98 \pm 2\%$ **VOLUME SOLIDS**  $98 \pm 2\%$ 

PRECEDING COATS Concrete: No.1615CP Vinyl Ester Sealer / Primer (for concrete)

Steel: No.1615HT Vinyl Ester Sealer / Primer (for high temperaturel)

SUBSEQUENT COATS No.1607HT Vinyl Ester Finish, HT

APPLICATION METHOD Airless Spray, Brush, Roller

STORAGE CONDITION Under 5°C

STORAGE SHELF LIFE 3 months / 5°C 1 month / 25°C 12 days / 30°C

NOTE 1. The thinner only for cleaning tools do not add to use.

> 2. The base and initiator must be stirred evenly, the applied surface must be smooth and without pinholes.

3. Avoid applying the paint in rainy weather or relative humidity above 85%.

4. Please wear gloves when application to avoid contacting the skin.

5. Hardener can be adjusted with temperature, consult the paint manufacturer.

EPDM701612HT V1.2

## YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443