



RAINBOW

RED LEAD PRIMER

PRODUCT NUMBER	906 (OP-92)
TYPE	Rust prevention primer based on alkyd resin and special resin with red lead rust resistant pigment.
USES	Used for steel structures.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying with good adhesion.2. Excellent resistance to water and oils.3. Excellent rust resistance, dipping in 3% salt water for 120 hours, result had no abnormal.4. Easy application.
FINISH	Flat
COLOR	Orange Red
HIDING POWER	Above 10.0 m ² /L
MASS DENSITY	Above 1.5 Kg/L
VISCOSITY	75~95 KU (25°C)
DRYING TIME	Set-to-touch 1/2 hr. Dry hard 4 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 90 microns Dry 40 microns
THEORETICAL COVERAGE	41.6 m ² /Gal 11.0 m ² /L 7.3 m ² /Kg
OVERCOATING INTERVALS	Min. 6 hrs.
NON-VOLATILE CONTENT	Above 70%
THINNER	No.805 Paint Thinner (OM-07)
THINNING RATE	5~10% (cleaning for tools not included)
PRECEDING COATS	No.908 Wash Primer (SP-01/02)
SUBSEQUENT COATS	Ready-Mixed Paints, Synthetic Enamels
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Spray, Brush, Roller
NOTE	<ol style="list-style-type: none">1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.3. Avoid applying the paint in rainy, humid weather or substrate temperature excessively high to 40°C or low to 10°C.4. Avoid applying to insufficient drying of previous paint coat.

EPDM090906XX V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443