



RAINBOW

RAINBOW C.R. T/S

PRODUCT NUMBER	SP-41 (RT-31~ 34)
TYPE	The topside paint based on chlorinated rubber with weather resistant pigment.
USES	Topcoat for dragnet ship's topside areas.
CHARACTERISTICS	<ol style="list-style-type: none">1. Very fast drying with excellent adhesion.2. Very good resistance to sea water.3. Very good resistance to mechanical damage.4. Very good resistance to weather.5. Very good resistance to floating oil on the sea.
FINISH	Gloss
COLOR	Desired colors
FLASH POINT	Above 26°C (80°F)
SPECIFIC GRAVITY	Above 1.2 Kg/L
VISCOSITY	70 ~ 85 KU (25°C)
DRYING TIME	Set-to-touch 1/2 hr. Dry hard 2 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 90 microns (3.6 mil) Dry 35 microns (1.4 mil)
THEORETICAL COVERAGE	42.0 m ² /Gal 11.1 m ² /L 9.3 m ² /Kg
OVERCOATING INTERVALS	Min. 4 hrs. (25°C)
VOLUME SOLIDS	Above 39 %
THINNER	No.1407 PCR Thinner (RP-71)
THINNING RATE	5~10 % (cleaning tools excluded)
PRECEDING COATS	SP-16 Rainbow C.R. A/C (RA-11) SP-32 Vinyl Anti-Corrosive (VA-11) (or according to our specific method of application)
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Airless Spray, Brush, Roller
NOTE	<ol style="list-style-type: none">1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.3. Avoid applying the paint in rainy or humid weather.

YUNG CHI PAINT & VARNISH MFG.CO.,LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443