RAINBOTHANE 751

Aliphatic Polyurethane Finish

PRODUCT NUMBER

RAINBOTHANE 751

TYPE

Two component aliphatic acrylic polyurethane finish.

CHARACTERISTICS

1. Unlimited recoatable.

2. Excellent resistance to atmospheric exposure conditions.

3. Excellent colour and gloss retention.

4. Non-chalking, non-yellowing.

5. Cures at temperatures down to -5° C.

GLOSS Gloss

COLORS White and various other colours Above 70 KU (mixture, 25°C) VISCOSITY **FLASH POINT** Above 23°C (mixture)

VOC Max. 400 g/L PRODUCT WEIGHT Above 1.3 kg/L

DRYING TIME Set-to-touch 1 hr. Dry hard 8 hrs. $(25^{\circ}C)$ **OPTIMUN FILM THICKNESS** Wet 100 ~ 120µ (Micron) Dry $50 \sim 60 \mu \text{ (Micron)}$

VOLUME SOLID

Above 50%

THEORETICAL COVERAGE **OVERCOATING TABLE**

36 m³/Gal 9.7 m²/L @ 60µ

Substrate temp.	-5 ℃	0 ℃	10 ℃	20 ℃	30 ℃	40 ℃
Min.	24 hrs	16 hrs	8 hrs	6 hrs	5 hrs	3hrs
Max.	unlimited					

MIXING RATIO Base: Hardener=17:3 (by volume)

POT LIFE 2 hrs (20°C) **THINNER** No.736 PU Thinner

THINNER RATE The mixing temperature for the base and hardener should be performed at above 15 ℃. Or

> else thinner should be added in order to achieve application viscosity, too much thinner will result in sagging. Well mix the base and hardener before any thinner is added $0\sim2\%$ (by

brush) $3\sim10\%$ (Airless).

RECOMMENDED SPEC. Please refer the painting specification

SHELF LIFE Minimum one year under normal storage condition

APPLICATION METHOD Airless spray, Brush

NOTE

- 1. Mix base and hardener according to the mixing ratio and stir thoroughly.
 - 2. Adhered water, grease and dust on substrate must be thoroughly clean.
 - 3. Steel; surface blast cleaned to ISO-Sa2½, roughness 30µ and above, or water-jet to VIS WJ
 - 4. Approved shop primer; sweep blasted or power tool cleaned to ISO SS St3 ·
 - 5. Substrate temperature should be 3[°]C above dew point, rainy day and relative humidity during application and curing should be below 85%, or job is to be stopped.
 - 6. Whilst application in the confine space, adequate ventilation must be maintenance.

EPDM3030751X V1.3

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443