



# RAINBOW

## ZINC CHROMATE PRIMER

PRODUCT NUMBER	907 ( OP-93)
TYPE	Rust prevention primer based on alkyd resin and special resin with zinc chromate pigment.
USES	Used for steel structures and non-ferrous metal.
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Excellent rust resistance, dipping in 3% salt water for 120 hours, result had no abnormal.</li><li>2. Excellent resistance to water and oils.</li><li>3. Very good adhesion.</li><li>4. Easy application.</li></ol>
FINISH	Flat
COLOR	Yellow
HIDING POWER	Above 8.0 m <sup>2</sup> /L
MASS DENSITY	Above 1.3 Kg/L
VISCOSITY	80~100 KU (25°C)
DRYING TIME	Set-to-touch 1 hr.                      Dry hard 6 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 90 microns                      Dry 40 microns
THEORETICAL COVERAGE	41.0 m <sup>2</sup> /Gal                      11.0 m <sup>2</sup> /L                      8.5 m <sup>2</sup> /Kg
OVERCOATING INTERVALS	Min. 8 hrs.
NON-VOLATILE CONTENT	Above 65%
THINNER	No.805 Paint Thinner ( OM-07 )
THINNING RATE	5~10% ( cleaning for tools not included )
PRECEDING COATS	No.908 Wash Primer ( SP-01/02 )
SUBSEQUENT COATS	Ready-Mixed Paints, Synthetic Enamels
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Spray, Brush, Roller
NOTE	<ol style="list-style-type: none"><li>1. Before application, stir paint evenly, and when paint is too thick, thinner within specified quantity can be added.</li><li>2. Adhered moisture, grease, dirt, damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.</li><li>3. Avoid applying the paint in rainy, humid weather or substrate temperature excessively high to 40°C or low to 10°C.</li><li>4. Avoid applying to insufficient drying of previous paint coat.</li></ol>

EPDM090907XX V1.0

# YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.  
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181  
FAX:886-7-8715443