EPOXY HIGH BUILT ALLOY PRIMER

PRODUCT NUMBER 1020HB

TYPE A two-pack, special alloy primer based on epoxy resin, hardener and special pigments.

USES Used for galvanized steel, aluminum, alum-alloy metal, stainless steel and tile after

cleaning.

CHARACTERISTICS 1. Very fast drying with excellent adhesion.

2. Very good adhesion with the galvanized steel, aluminum, stainless steel and tile.

3. Very good resistance to corrosion and abrasion.

4. The paint film exposed for a half year without ageing.

FINISH Flat

COLOR Yellowish Green . Gray

FLASH POINT Above 20°C (68°F, mixture) MASS DENSITY Above 1.35 Kg/L (mixture)

VISCOSITY Above 75~95KU (mixture, 25°C)

DRYING TIME Set-to-touch 2 hrs. Dry hard 10 hrs. Fully cured 7 days. (25°C)

OPTIMUM FILM THICKNESS Wet 142 microns Dry 100 microns

37.8 m²/Gal 6.9 m²/L 5.1 m²/Kg 26

OVERCOATING INTERVALS Min. 8 hrs. Max. 6 months MIXING RATIO Base: Hardener = 90:10 (by wt.)

NON-VOLATILE CONTENT Above 69% (mixture)

POT LIFE Above 6 hrs. (mixture, 25°C)

THINNER No.1005 Epoxy Thinner (SP-12) THINNING RATE 5~10% (cleaning tools excluded)

SUBSEQUENT COATS Epoxy, Polyurethane, Fluorocarbon system or others we suggested.

SURFACE TREATMENT SIS Sa2, SSPC SP1, SSPC SP3

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

APPLICATION METHOD Airless Spray, Brush(for small areas only)

FOR AIRLESS SPRAY Graco 617, 719 Tip size

> 3~4 Kg/cm² Air pressure

18~23 sec. (Ford Cup No.4) Viscosity

NOTE 1. Mix base and hardener according to the mixing ratio and stir thoroughly.

2. Avoid applying paint in rainy or humid weather particularly a wet surface must be

thoroughly dried.

3. All equipment must be cleaned immediately after use.

4. The topcoat must be applied within overcoating intervals to avoid dirt effect the adhesion. If dirt is adhered on surface of paint film, the surface treatment must be done and then can be applied topcoat.

5. Do not to be used in the lining of storage tank.

EPDM101020HB V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.