EPOXY MIDDLE COATING

PRODUCT NUMBER 1060

FINISH

TYPE A two-pack, middle paint based on epoxy resin and special hardener with special

pigment.

USES Used for steel structures that have been coated with inorganic zinc rich primer, such

as steel pipes, steel frame, bridges, plant facilities etc to prevent the blistering, also

used for cement wall and cement products.

CHARACTERISTICS 1. Tough and hard film, rich flexible and adhesion.

2. Excellent adhesion with inorganic zinc rich primer, it can fill holes on surface of

zinc rich paint to prevent topcoat to blistering.

3. Excellent abrasion resistance and electrical insulation. 4. Excellent resistance to oils, solvents and chemicals.

COLOR White, grey, reddish brown

HIDING POWER Above 8 m²/L (mixture)

MASS DENSITY Above 1.45 Kg/L

VISCOSITY 70~90 KU (mixture, 25°C)

DRYING TIME Set-to-touch 1.5 hrs. Dry hard 6 hrs. Fully cured 7 days (25°C)

> Wet 80 microns Dry 40 microns 47.3 m³/Gal 12.5 m²/L 8.3 m³/Kg

OVERCOATING INTERVALS Min. 8 hrs.

OPTIMUM FILM THICKNESS

THEORETICAL COVERAGE

MIXING RATIO Base : hardener = 92.1 : 7.9 (by wt.)

NON-VOLATILE CONTENT Above 70% (mixture, 25°C) **POT LIFE** 8 hrs. (mixture, 25°C)

VOLUME SOLIDS 53±3%

No.1005 Epoxy Thinner (SP-12) **THINNER** THINNING RATE 5~15% (cleaning tools excluded)

PRECEDING COATS Steel: No.1006 Epoxy Zinc Rich Primer (EP-03)

> No.1011 Inorganic Zinc Rich Primer (IZ-01) Concrete: No.1073 Epoxy Clear Cement Primer

No.1073PC Epoxy Cement Primer

No.1002 Epoxy Primer, white

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

Airless Spray, Brush

1. Mix base and hardener according to the mixing ratio and stir thoroughly then keep static about 10~20 minutes before use.

2. Adhered moisture, grease, dirt, dust, rust and corrosion salts on substrate must be removed thoroughly.

3. Avoid applying the paint in rainy weather or relative humidity exceeded 85%, particularly a wet surface must be thoroughly dried.

4. All equipment must be cleaned immediately after use.

5. When used inside tanks, sufficient ventilation must be provided.

EPDM101060XX V1.1

APPLICATION METHOD

NOTE

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443