VINYL MARINE FINISH

PRODUCT NUMBER SP-34 (VF-51)

TYPE Finish paint based on vinyl resin with weather resistant pigment.

USES Topcoat for superstructures, deck fittings and

CHARACTERISTICS 1. Very fast drying with excellent adhesion to vinyl A/C.

2. Very good resistance to sea water and oil.

3. Very good resistance to weather.

4. Tough and flexible.

FINISH Gloss

DRYING TIME Set-to-touch 1/2 hr. Dry hard $2 \text{ hrs.} (25^{\circ}\text{C})$ OPTIMUM FILM THICKNESS Wet 95 microns (3.8 mil) Dry 35 microns (1.4 mil)

THEORETICAL COVERAGE 40.0 m²/Gal 10.5 m²/L 10.5 m²/Kg

OVERCOATING INTERVALS Min. 3 hrs. (25 $^{\circ}$ C) VOLUME SOLIDS Above 37 $^{\circ}$

THINNER SP-36 Vinyl Thinner (VF-61)

THINNING RATE 5~10 % (cleaning tools excluded)
PRECEDING COATS SP-32 Vinyl Anti-Corrosive (VA-11)

SP-30 Vinyl Red Lead Primer

Epoxy primers

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

APPLICATION METHOD Airless Spray, Brush

NOTE Application of vinyl paints should not be done in damp foggy, or rainy weather, and the

relative humidity should never exceed 85%.