## VINYL BOOTTOPING, BLACK

PRODUCT NUMBER SP-25 (VF-53)

TYPE The boottoping paint based on vinyl resin with weather resistant pigment.

USES Topcoat for boottop areas.

CHARACTERISTICS 1. Very fast drying with excellent adhesion to vinyl A/C.

2. Very good resistance to sea water and oil.

3. Very good resistance to weather.

4. Tough and flexible.

FINISH Gloss COLOR Black

FLASH POINT Above 8°C (46°F) SPECIFIC GRAVITY Above 1.0 Kg/L VISCOSITY 70  $\sim$  85 KU (25°C)

DRYING TIME Set-to-touch 1/2 hr. Dry hard  $2 \text{ hrs.} (25^{\circ}\text{C})$  OPTIMUM FILM THICKNESS Wet 95 microns (3.8 mil) Dry 35 microns (1.4 mil)

THEORETICAL COVERAGE 40.0 m²/Gal 10.5 m²/L 10.5 m²/Kg

OVERCOATING INTERVALS Min. 3 hrs.  $(25^{\circ})$  VOLUME SOLIDS Above 37 %

THINNER SP-36 Vinyl Thinner (VF-61)

THINNING RATE  $5\sim10~\%$  (cleaning tools excluded) PRECEDING COATS SP-32 Vinyl Anti-Corrosive (VA-11)

SP-30 Vinyl Red Lead Primer

**Epoxy primers** 

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

APPLICATION METHOD Airless Spray, Brush

NOTE Application of vinyl paints should not be done in damp foggy, or rainy weather, and the

relative humidity should never exceed 85%.