



RAINBOW

RAINBOLIC 21

Acrylic Primer

PRODUCT NUMBER	RAINBOLIC 21
TYPE	Acrylic primer/sealer
CHARACTERISTICS	<ol style="list-style-type: none">1. Anti-corrosive primer/sealer.2. Resistant to well designed/controlled cathodic protection.3. Fast drying.4. Compatible with antifouling.5. Easy application
GLOSS	Flat
COLORS	Silver ,Silver Red
VOLATILE ORGANIC COMPOUND CONTENT	VOC 450 (g/l) below
PRODUCT WEIGHT	Above 1.1 kg/L.
DRYING TIME	Set-to-touch 1 hrs Dry hard 4 hrs (25°C) (50μ)
OPTIMUM FILM THICKNESS	Wet 78 ~ 167μ (Micron) Dry 35 ~ 75μ (Micron)
VOLUME SOLID	45 ±2%
THEORETICAL COVERAGE	50.5 m ² /Gal 13.3 m ² /L @ 35μ
OVERCOATING TABLE	least 3 hours (25°C) □
THINNER	RP-71 rubber thinner
THINNER RATE	0~2% (by bush and roller) 0~3% (Airless)
RECOMMENDED SPEC.	Please refer the painting specification
SHELF LIFE	Minimum two years under normal storage condition
APPLICATION METHOD	Airless spray, Bush and Roller
NOTE	<ol style="list-style-type: none">1. Adhered water, grease and dust on substrate must be thoroughly clean.2. Substrate temperature should be 3°C above dew point, rainy day and relative humidity during application and curing should be below 85%, or job is to be stopped.3. Whilst application in the confine space, adequate ventilation must be maintenance.

EPDM3030021X V1.2

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443