EPOXY COATING, SOLVENTLESS

PRODUCT NUMBER 1015

GLOSS

TYPE A two-pack, solventless paint based on solventless epoxy resin and hardener with

chemicals resistant pigment.

USES Used for the storage tank lining and the plant facilities of chemical factories, power

plants, steel plants etc.

CHARACTERISTICS 1. Tough and hard film with very good adhesion.

2. 200µ pinhole-less paint film with one coat.

3. Excellent resistance to water and oils.

4. Excellent resistance to oils, chemicals and corrosion.

5. Excellent resistance to mechanical damage and electrical insulation.

Above 85%

COLOR Refer to colors card

Above 8 m²/L (mixture, depending on colors) **HIDING POWER**

MASS DENSITY Above 1.35 Kg/L (mixture)

90~110 KU (25°C) VISCOSITY

DRYING TIME Set-to-touch 6 hrs. Dry hard 18 hrs. Fully cured 7 days (25°C)

OPTIMUM FILM THICKNESS Wet 375 microns Dry 350 microns THEORETICAL COVERAGE 10.2 m³/Gal 2.7 m²/L 2.3 m²/Kg **OVERCOATING INTERVALS** Min. 24 hrs. Max. 7 days (25°C)

MIXING RATIO Base: hardener = 80: 20 (by wt.)

NON-VOLATILE CONTENT Above 95% (mixture) **POT LIFE** 1/2 hr. (mixture, 25°C)

THINNER No.1005 Epoxy Thinner (SP-12) (only cleaning tools)

PRECEDING COATS No.1073 Epoxy Clear Cement Primer

STORAGE SHELF LIFE Minimum 1 year under normal storage conditions.

APPLICATION METHOD Trowel, Brush NOTE

1. Mix base and hardener according to the mixing ratio and stir thoroughly, it must be used up within 5 minutes.

> 2. Adhered moisture, grease, dirt, dust, rust and corrosion salts on substrate must be removed thoroughly.

3. Avoid applying the paint in rainy weather or relative humidity exceeded 85%. particularly a wet surface must be thoroughly dried.

4. All equipment must be cleaned immediately after use.

5. The surface of cement wall or cement products must be thoroughly dried then can be applied.

6. When overcoating interval is exceeded, paint surface must be roughened to ensure adhesion.

EPDM101015XX V1.1

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443