



### Zinc Rich Silicate

Substrate temp.	-5 °C	0 °C	10 °C	20 °C	30 °C	40 °C
Minimum interval	24 hours	24 hours	18 hours	12 hours	6 hours	4 hours
Maximum interval	unlimited					