## **GLOSS EMULSION PAINTS**

PRODUCT NUMBER 650

**TYPE** The gloss emulsion paint based on excellent water resistant, alkali resistant

water-based resin with weather resistant pigment and additives.

**USES** Used for indoor cement walls to decoration and protection such as office buildings,

hotels, public places, hospitals, shops, houses etc.

**CHARACTERISTICS** 1. Use water as the solvent without pollution and fire danger.

2. Use water as a dilution to be able to reduce the construction cost.

3. High gloss, hard film with smooth appearance.

4. Excellent resistance to water and alkalis.

**GLOSS** High gloss

COLOR White or various colors

HIDING POWER Above 10.0 m<sup>2</sup>/L MASS DENSITY Above 1.2 Kg/L VISCOSITY 85 ~ 105 KU (25°C)

DRYING TIME Set-to-touch 1/2 hr. Dry hard 3 hrs. (25°C)

**OPTIMUM FILM THICKNESS** Wet 90 microns Dry 35 microns

THEORETICAL COVERAGE 42.0 m²/Gal 11.0 m<sup>2</sup>/L 9.3 m³/Kg

**OVERCOATING INTERVALS** Min. 4 hrs. **THINNER** Tap water THINNING RATE 5~10%

PRECEDING COATS No.410-1 Emulsion Primer

STORAGE SHELF LIFE Minimum 3 years under normal storage conditions.

APPLICATION METHOD Spray, Brush, Roller.

NOTE 1. Before application, stir paint thoroughly, and when paint is too thick, the tap

water within specified quantity can be added.

2. Adhered moisture, grease, and dirt on substrate must be cleaned thoroughly.

3. Do not use this paint to mix with other colored paints, if required, please use

No.411~412 Acrylic Emulsion Paints to avoid color fading.

4. The application must be waited for 2 to 3 weeks until the walls were completely dry off and the moisture content under 12%, because the new constructed cement walls contain a lot of moisture and free alkaline substances that may

reduce paint film performance and adhesion.

EPDM410650X1 V1.3

## YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan. TEL:886-7-8713181 http://www.rainbowpaint.com.tw

FAX:886-7-8715443